

MILL TEST REPORT

Cement Type: **CSA Type GU**
Low Alkali Portland Cement

Plant: **Delta, BC**

Certificate #:	D1-387
-----------------------	---------------

Production Period:	Jul 01 2010 Jul 31 2010	Test Result	CSA A3001 Specification
SiO2 (%)	CSA A3003	20.0	-
Al2O3 (%)	CSA A3003	4.78	-
Fe2O3 (%)	CSA A3003	3.69	-
CaO (%)	CSA A3003	64.4	-
MgO (%)	CSA A3003	0.84	max. 5.0
SO3 (%)	CSA A3003	2.77	max. 3.0
Na2O (%)	CSA A3003	0.32	-
K2O (%)	CSA A3003	0.38	-
TiO2 (%)	CSA A3003	0.24	-
C3S (%)	ASTM C150	65	-
C2S (%)	ASTM C150	8	-
C3A (%)	CSA A3003	6.4	-
C4AF (%)	ASTM C150	11.2	-
Equivalent Alkalies (%)	ASTM C150	0.57	-
Loss on Ignition (%)	CSA A3003	2.8	max. 3.0
Insoluble Residue (%)	CSA A3003	0.20	max. 1.5
Free Calcium Oxide (%)	CSA A3003	0.38	-
Vicat Setting Time			
Initial (minutes)	CSA A3004-B2	98	min. 45 max. 375
Final (minutes)	CSA A3004-B2	201	-
Blaine Fineness (m2/kg)	ASTM C204	398	-
+325 mesh	CSA A3004-A3	1.5	max. 28
Air Content (%)	CSA A3004-C4	7.05	-
Autoclave Expansion (%)	CSA A3004-B5	-0.01	max. 1.0
Compressive Strength		MPa / psi	
3 Day	CSA A3004-C2	30.3 / 4387	min. 14.5
7 Day	CSA A3004-C2	35.9 / 5208	min. 20.0
28 Day (previous month)	CSA A3004-C2	42.5 / 6169	min. 26.5

This will certify that the above described cement meets the standard chemical and physical requirements of CSA Specification A3001-08 for Type GU Portland Cement.

