

## MILL TEST REPORT

Cement Type: **ASTM Type III, AASHTO Type III, CSA Type HE**  
**High Early Strength, Low Alkali Portland Cement**

Plant: **Delta, BC**

Certificate #: **D6-002**

Production Period:	Sep 01 2011		Test	ASTM / AASHTO	CSA
	Sep 30 2011		Result	C150 / M85	A3001
				Specification	Specification
SiO <sub>2</sub> (%)	ASTM C114	CSA A3003	20.3	-	-
Al <sub>2</sub> O <sub>3</sub> (%)	ASTM C114	CSA A3003	4.80	-	-
Fe <sub>2</sub> O <sub>3</sub> (%)	ASTM C114	CSA A3003	3.73	-	-
CaO (%)	ASTM C114	CSA A3003	64.1	-	-
MgO (%)	ASTM C114	CSA A3003	0.81	max. 6.0	max. 5.0
SO <sub>3</sub> (%)	ASTM C114	CSA A3003	3.04	max. 3.5	max. 3.5
Na <sub>2</sub> O (%)	ASTM C114	CSA A3003	0.32	-	-
K <sub>2</sub> O (%)	ASTM C114	CSA A3003	0.36	-	-
TiO <sub>2</sub> (%)	ASTM C114	CSA A3003	0.25	-	-
C <sub>3</sub> S (%)	ASTM C150	ASTM C150	59	-	-
C <sub>2</sub> S (%)	ASTM C150	ASTM C150	12	-	-
C <sub>3</sub> A (%)	ASTM C150	CSA A3003	6.2	max. 15	-
C <sub>4</sub> AF (%)	ASTM C150	ASTM C150	11.0	-	-
<b>Total Alkalis (%)</b>	ASTM C114	CSA A3003	<b>0.56</b>	max. 0.60	-
<b>Loss on Ignition (%)</b>	ASTM C114	CSA A3003	<b>2.44</b>	max. 3.0	max. 3.0
<b>Insoluble Residue (%)</b>	ASTM C114	CSA A3003	<b>0.12</b>	max. 0.75	max. 1.5
<b>Free Calcium Oxide (%)</b>	ASTM C114	CSA A3003	<b>0.33</b>	-	-
<b>CO<sub>2</sub> in Cement (%)</b>	ASTM C114		<b>1.41</b>	-	-
<b>CaCO<sub>3</sub> in Limestone (%)</b>	ASTM C114		<b>98</b>	min. 70	-
<b>Limestone in Cement (%)</b>	ASTM C150		<b>3.3</b>	max. 5.0	-
<b>Blaine Fineness (m<sup>2</sup>/kg)</b>	ASTM C204	ASTM C204	<b>543</b>	-	-
<b>+325 mesh</b>	ASTM C430	CSA A3004-A3	<b>0.56</b>	-	-
<b>Vicat Setting Time</b>					
<b>Initial (minutes)</b>	ASTM C191	CSA A3004-B2	<b>79</b>	min. 45 max. 375	min. 45 max. 250
<b>Final (minutes)</b>	ASTM C191	CSA A3004-B2	<b>179</b>	-	-
<b>Air Content (%)</b>	ASTM C185	CSA A3004-C4	<b>7.29</b>	max. 12	-
<b>Autoclave Expansion (%)</b>	ASTM C151	CSA A3004-B5	<b>-0.04</b>	max. 0.80	max. 1.0
<b>Compressive Strength</b>			<b>MPa / psi</b>		
<b>1 Day</b>	ASTM C109/109M	CSA A3004-C2	<b>25.0 / 5752</b>	min. 12.0	min. 13.5
<b>3 Day</b>	ASTM C109/109M	CSA A3004-C2	<b>39.7 / 5752</b>	min. 24.0	min. 24.0
<b>28 Day (previous month)</b>	ASTM C109/109M	CSA A3004-C2	<b>51.1 / 7410</b>	-	-

This will certify that the above described cement meets the standard requirements and optional Low Alkali chemical requirements of ASTM Specification C-150 and AASHTO Specification M-85 for Type III Portland Cement, and CSA Specification A3001 and A5 for Type HE Portland Cement.  
 Note that CSA Specification A3001 superseded CSA Specification A5.

Siu Kei (S.K.) Ng  
 Plant Chemist



October 11, 2011